













ferrierite_polished_coat



Name	Date	Time	HV [kV]	Mag	WD [mm]
Ch 0	10/8/2019	8:49:23 AM	20.0 keV	1000x	10.0 m




Name	Date	Time	HV [kV]	Mag	WD [mm]
ferrierite polished coated	10/8/2019	8:49:23 AM	20.0 keV	1000x	10.0 mm



Date	Time	HV [kV]	Mag	WD [mm]
10/8/2019	8:49:23 AM	20.0 keV	1000x	10.0 mm

ferrierite_polished_coatedsid



ferrierite_polished_coatedside.xlsx

Element	At. No.	Mass [%]	Mass Norm. [%]	Atom [%]
Carbon	6	31.51	26.22	37.47
Oxygen	8	46.62	38.80	41.63
Sodium	11	0.91	0.76	0.57
Magnesium	12	0.50	0.42	0.29
Aluminium	13	6.05	5.04	3.21
Silicon	14	29.79	24.79	15.15
Potassium	19	3.96	3.30	1.45
Calcium	20	0.34	0.28	0.12
Iron	26	0.46	0.38	0.12
		120.15	100.00	100.00