













ferrierite_polished_unc



Name	Date	Time	HV [kV]	Mag	WD [mm]
Ch 0	10/8/2019	8:53:55 AM	20.0 keV	1000x	10.1 m




Name	Date	Time	HV [kV]	Mag	WD [mm]
ferrierite polished uncoated	10/8/2019	8:53:55 AM	20.0 keV	1000x	10.1 mm



Date	Time	HV [kV]	Mag	WD [mm]
10/8/2019	8:53:55 AM	20.0 keV	1000x	10.1 mm

ferrierite_polished_uncoateds



ferrierite_polished_uncoatedside.xlsx

Element	At. No.	Mass [%]	Mass Norm. [%]	Atom [%]
Carbon	6	6.74	6.80	11.06
Oxygen	8	46.88	47.27	57.77
Sodium	11	1.02	1.03	0.88
Magnesium	12	0.39	0.39	0.31
Aluminium	13	6.58	6.64	4.81
Silicon	14	31.82	32.09	22.34
Potassium	19	4.88	4.92	2.46
Calcium	20	0.39	0.39	0.19
Iron	26	0.48	0.48	0.17
		99.18	100.00	100.00